

COLORES / COLOURS



SAND
60x120, 60x60



SLATE
60x120, 60x60



WHITE
60x120, 60x60

PORCELÁNICO — BIA PORCELÁNICO

Model	Size	1	2	3	4	5	6	7	8	9	10	11	12	13	14	15	16
BURLI SAND 60X120	60x120 24"X48"R	Mohs 8	Complies	<= 0,5%	Complies	> 35N/mm2	Class 4	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-
BURLI SAND 60X60	60x60 24"X24"R	Mohs 8	Complies	<= 0,5%	Complies	> 35N/mm2	Class 4	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-
BURLI SLATE 60X120	60x120 24"X48"R	Mohs 8	Complies	<= 0,5%	Complies	> 35N/mm2	Class 2	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-
BURLI SLATE 60X60	60x60 24"X24"R	Mohs 8	Complies	<= 0,5%	Complies	> 35N/mm2	Class 2	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-
BURLI WHITE 60X120	60x120 24"X48"R	Mohs 9	Complies	<= 0,5%	Complies	> 35N/mm2	Class 4	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-
BURLI WHITE 60X60	60x60 24"X24"R	Mohs 8	Complies	<= 0,5%	Complies	> 35N/mm2	Class 4	6,6-10-6/°C	Complies	Complies	Complies	GLA	GHA	GA	Class 5	Class 1	-

1. Surface hardness degree (MOHS) (EN 101)

2. Dimensions and superficial aspect (UNE EN ISO 10545-2)

3. Water absorption (%) (UNE EN ISO 10545-3)

4. Breaking strength (N) (UNE EN ISO 10545-4)

5. Modulus of rupture (N/mm²) (UNE EN ISO 10545-4)

6. Abrasion resistance (UNE EN ISO 10545-7)

7. Lineal thermic expansion coefficient (UNE EN ISO 10545-8)

8. Thermal shock resistance (UNE EN ISO 10545-9)
9. Cracking resistance (UNE EN ISO 10545-11)

10. Frost resistance (UNE EN ISO 10545-12)

11. Chemical resistance — weak acids/bases (UNE EN ISO 10545-13)

12. Chemical resistance — strong acids/bases (UNE EN ISO 10545-13)

13. Chemical resistance — Domestic cleaning (UNE EN ISO 10545-13)

14. Stains resistance (UNE EN ISO 10545-14)

15. Slip resistance (UNE ENV 12633/2003 — DIN 51130/2010)

16. DCOF (DCOF)

PACKAGING

Size	Box			Pallet			Euro Pallet		
	PCS	M²	KG	BOX	M²	KG	BOX	M²	KG
60x120 (24"X48"R)	3	2	24	0	0	0	29	62	1100
60x60 (24"X24"R)	4	1	37	0	0	0	40	57	960